## A Pigment of Your Imagination



## **TECHNICAL DATA SHEET**

Date:01.11.2020 Revision: 02

Product Description				
C.I Generic Name	PIGMENT RED 170 (F5RK)		NPPL Product Code	IN-9013
C.I No.	12475		CAS No.	2786-76-7
EINECS No.	220-509-3		Chemical Type	Naphthol AS
Molecular Formula	C26H22N4O4		Molecular Weight	243.28
Chemical Name: 4-[[4-(aminocarbonyl)phenyl]azo]-N-(2-ethoxyphenyl)-3-hydroxynaphthalene-2-carboxamide				

Physical Properties		
Sieve Residue (PPM) Max	1000	
Oil Absorption (gms)	55 - 70	
Bulk Density (gm/ml)	0.20- 0.35	
Salt Content (%) Max.	1	
Moisture Content (%) Max	1	

Fastness properties		
Heat °C		200
Light	Mass Tone	8
Light	Tint Tone	7
Weather	Mass Tone	
Weather	Tint Tone	
Migration		5

Application		
NC alcohol / Polyuvinyl butyral	•	
Water based	0	
UV curing ( Flexo) / Decorative laminates /	•	
UV curing (Offset)	•	
Sheetfed / Silkscreen / Metal	•	
	•	
	•	
•	Suitable	
0	Limited Suitability	

Mass Tone: 5%	Tint Tone: 1:10 Ratio

Solvent Fastness properties		
Water	5	
Ethanol	5	
Ethyl Acetate	5	
MEK	5	
Acid	5	
Alkali	5	

Specification	
Coloristic properties - Tint	Strength: ±5%
Coloristic properties - Tint	DA,DB,DE,DC,DH,DL: ±1
Light fastness: Scale 1-8	1~Poor & 8 ~ Excellent
Weather fastness : Scale 1-5	1~Poor & 5 ~ Excellent
Overspray: Scale 1-5	1~Poor & 5 ~ Excellent
Solvent Fastness: Scale 1-5	1~Poor & 5 ~ Excellent

Note: The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.









NAVPAD PIGMENTS PVT. LTD.

A Govt. Of India Recognized Star Export House

Regd. Office & Factory: 1196/1/A & B, Ghumasan Patia Road, Chhatral - Mehsana Highway, Rajpur - 382715, Gujarat, India

T: +91-982-503-1388 / +91-2764-278338

E: exports@navpadpigments.com W: www.navpadpigments.com