## A Pigment of Your Imagination




## **TECHNICAL DATA SHEET**

Date:01.11.2020 Revision: 02

Product Description				
C.I Generic Name	PIGMENT RED 22		NPPL Product Code	9064
C.I No.	12315		CAS No.	6448-95-9
EINECS No.	229-245-3		Chemical Type	Napthol
Molecular Formula	C24H18N4O4		Molecular Weight	426.42

Chemical Name: AKA404; Fast Red N; C.I. 12315; Scarlet BG; PIGMENT RED 22; Solvent Green 5B;C.I.PIGMENTRED22;3117 Fast Scarlet N;Fast Brilliant Red N;BRILLIANT FAT SCARLET

Physical Properties		
Sieve Residue (PPM) Max	1000	
Oil Absorption (gms/100 grms)	50+/-10	
Bulk Density (gm/ml)	0.20-0.35	
Salt Content (%) Max.	1	
Moisture Content (%) Max	1	



Fastness properties		
Heat °C		180
Light	Mass Tone	6
Light	Tint Tone	5
Weather	Mass Tone	4
Weather	Tint Tone	5
Overspray		5
Migration		4

Specification	
Coloristic properties - Tint	Strength: ±5%
Coloristic properties - Tint	DA,DB,DE,DC,DH,DL: ±1
Light fastness: Scale 1-8	1~Poor & 8 ~ Excellent
Weather fastness : Scale 1-5	1~Poor & 5 ~ Excellent
Overspray: Scale 1-5	1~Poor & 5 ~ Excellent
Solvent Fastness: Scale 1-5	1~Poor & 5 ~ Excellent

Application		
PP / HDPE / LDPE	•	
PVC	•	
Textile	•	
•	Suitable	
0	Limited Suitability	

Note: The colors above have been generated electronically and should therefore not be used for comparison purposes. The colors are meant to give a first impression of the colorant shade.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our Product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.















Regd. Office & Factory: 1196/1/A & B, Ghumasan Patia Road, Chhatral - Mehsana Highway, Rajpur - 382715, Gujarat, India

T: +91-982-503-1388 / +91-2764-278338

E: exports@navpadpigments.com W: www.navpadpigments.com